

LEDRACTIVE DF	%		SOLUBILITY 30°C 60°C	LIGHT 1/1	WASH TEST AATCC TM 61-IIA COLOR CHANGE	CROCKTEST AATCC TM 8		PERSPIRATION AATCC TM 15				OPTIMUM DYEING TEMPERATURE °C
						DRY	WET	ACID		ALKALINE		
								COLOR CHANGE	STAINING COTTON	COLOR CHANGE	STAINING COTTON	
BR. BLUE RX 150%	0.5		100 100	5-6	5	5	4	5	5	5	5	60
BR. BLUE DF-BL New	0.5		100 100	5	4	4-5	3	2-3	4-5	4-5	4	60
BLUE BB 133%	0.5		40 50	5-6	3-4	4-5	3-4	3	5	4-5	4	60
BLUE BRF 150%	0.5		100 100	5-6	4-5	4-5	3-4	4	4-5	4-5	4	60-80
TURQUOISE G 266%	0.5		100 100	5	3	5	4	2	5	4	5	80
BLUE DF-LF	0.5		80 100	5-6	4-5	5	3-4	4-5	5	4-5	4	60-80
BLUE DF-BN	0.5		100 100	5	4-5	5	3-4	4-5	5	4-5	4	60-80
NAVY BLUE GBS 150%	0.5		80 100	4-5	5	4-5	3-4	4	5	4	4	60-80
NAVY BLUE DF-RGB 150%	0.5		100 100	3-4	4-5	4-5	3	4-5	5	4	5	60-80
NAVY BLUE GG	0.5		80 100	4-5	5	5	3-4	5	5	4	4-5	60-80
BLACK T-2B 150%	8		100 100	3-4	5	4-5	2-3	5	5	5	4	60
BLACK GSP	8		100 100	5-6	4-5	4-5	3	4-5	4-5	4	4-5	60
BLACK N 150%	8		100 100	5	5	4-5	3	5	4-5	4-5	4-5	60

LEDRACTIVE DF	%		SOLUBILITY 30°C 60°C	LIGHT 1/1	WASH TEST AATCC TM 61-1/A COLOR CHANGE	CROCKTEST AATCC TM 8		PERSPIRATION AATCC TM 15				OPTIMUM DYEING TEMPERATURE °C
						DRY	WET	ACID		ALKALINE		
								COLOR CHANGE	STAINING COTTON	COLOR CHANGE	STAINING COTTON	
YELLOW DF-3GL 150%	0.5		80 80	6	5	5	4	5	5	4-5	4-5	60-80
G. YELLOW DF-RL 150%	0.5		40 80	5-6	5	4-5	4	5	5	4	4	60-80
ORANGE DF-2RL 150%	0.5		30 60	5-6	4	4-5	4	4	4	4	3	60-80
ORANGE DF-3G	0.5		100 100	4-5	4	4-5	4	4-5	4	5	5	60-80
ORANGE SP	0.5		80 80	4-5	4	4-5	3-4	4	4-5	4	4	60-80
SCARLET DF-2G	0.5		100 100	5	4	4-5	3-4	4	4-5	4-5	5	60-80
SCARLET DF-HP	0.5		100 100	5	4-5	4-5	4	3-4	4-5	4-5	5	60-80
RED DF-3BL	0.5		100 100	6	4-5	4-5	3-4	5	4-5	5	5	60-80
RED DF-B 200%	0.5		100 100	4-5	5	4-5	2-3	5	4-5	5	5	60-80
RED DF-RBL 133%	0.5		100 100	4-5	4-5	4-5	3-4	4-5	4	4-5	4	60
RED DF-4BL 150%	0.5		100 100	5	4-5	4-5	3	5	4-5	4-5	4	60-80
RED DF-6BL New	0.5		100 100	5-6	4-5	4-5	3	4	4-5	4	4	60-80
RUBINE DF-7BL	0.5		100 100	5	4-5	4-5	3-4	4-5	4	3-4	3-4	60-80